

ProRox® MA 930^{NA}



Old name: ROXUL RHT® 40 WRAP

Product description & application

ProRox® MA 930^{NA} is a rolled mineral wool (stone wool) thermal insulation wrap/mat for intermediate to high temperature industrial applications.

Product properties in accordance with ASTM C612

	Performance							Norms
Thermal conductivity	T _m (°F)	100	200	300	400	500	600	ASTM C177
	λ (BTU.in/hr.ft².°F)	0.26	0.30	0.37	0.45	0.55	0.67	
	T _m (°C)	50	100	150	200	250	300	
	λ (W/mK)	0.037	0.043	0.053	0.065	0.079	0.097	
Maximum Service Temperature	Hot Surface Performance: 1200 °F- (650 °C)							ASTM C411
	Non-Combustible							ASTM E136 / CAN4 S114
	Linear Shrinkage: ≤ 2 % at 1200 °F- (650 °C)							ASTM C356
Reaction to fire	Surface burning characteristics Flame spread index = 0 ; Smoke development index = 0							ASTM E84 (UL 723) CAN/ULC S102
Density	Actual Density = 3.5 lb/ft³ - (56 kg/m³) Nominal Density = 4.0 lb/ft³							ASTM C303
Corrosion resistance **	Stress Corrosion Cracking Tendency of Austenitic Stainless Steel = Passed Corrosion of Steel = Passed							ASTM C692 ASTM C665
Chemical Analysis **	(Salts: Cl ⁻ , F ⁻ , Na ⁺ , SiO ₄ ⁴⁻) Results fall within acceptability limits of ASTM C795							ASTM C795 / ASTM C871
Thermal Resistance	R-Value / inch @ 75 °F			4.0 hr. ft².°F/BTU				ASTM C518 (C177)
	RSI value / 25.4mm @ 24 °C			0.71 m² K/W				
Water Absorption/ Vapor Sorption	< 1 % Weight							ASTM C1104
Compliance	Complies with Type: VII							ASTM C553
	ROXUL offers a wide range of facings, dimensions and thicknesses. Please contact ROXUL for further information.							

Surface Burning Characteristics: UL Listed to Canadian standard CAN/ULC S102 ; UL Classified to UL 723



NOTE: ** Provisions for lot testing may be required, consult manufacturer.
 As ROXUL® Inc has no control over installation design and workmanship, accessory materials or application conditions, ROXUL® Inc. does not warranty the performance or results of any installation containing ROXUL® Inc's products. ROXUL® Inc's overall liability and the remedies available are limited by the general terms and conditions of sale. This warranty is in lieu of all other warranties and conditions expressed or implied, including the warranties of merchantability and fitness for a particular purpose.

©/TM: US - owner Rockwool International A/S used under license; Canada - owner Roxul Inc.